



HECHO EN POLONIA

COLLECTION NAME		COLOUR	BODY	SURFACE	
NICKWOOD		MARRONE, BEIGE	COLOUR BODY	STRUCTURE	
PHYSICAL PROPERTIES		NORM	REQUIREMENTS	MEAN VALUE ACHIEVED	
	WATER ABSORPTION [%]	PN-EN ISO 10545-3	< 0,5	< 0,1	
	MODULUS OF RUPTURE [N/mm ²]	PN-EN ISO 10545-4	≥ 35	≥ 45	
	BREAKING STRENGTH [N]	PN-EN ISO 10545-4	> 700	> 1300	
	FROST RESISTANCE	PN-EN ISO 10545-12	required	resistant	
	ABRASION RESISTANCE	PN-EN ISO 10545-7	required	BEIGE	14/12000
				MARRONE	13/1500
	RESISTANCE TO HOUSEHOLD CHEMICALS	PN-EN ISO 10545-13	min. B	Ammonium chloride solution	A
				Sodium hypochlorite solution	A
	RESISTANCE TO HIGH OR LOW CONCENTRATION OF ACIDS OR ALKALIS	PN-EN ISO 10545-13	declared	Hydrochloric acid solution, 3%	LA
				Citric acid solution 100g/l	LA
				Potassium hydroxide solution, 30g/l	LA
				Hydrochloric acid solution, 18%	HA
				Lactic acid solution, 5%	HA
				Potassium hydroxide solution, 100g/l	HA
	RESISTANCE TO STAINING	PN-EN ISO 10545-14	min. 3	5	
	CRAZING RESISTANCE	PN-EN ISO 10545-11	required	resistant	
DCOF		ANSI A326.3	> 0,42	0,48	
		PN-EN ISO-10545-9	required	resistant	

REFERENCE DOCUMENT: DECLARATION OF PERFORMANCE NO. 7A/02 CPR

GANTE
Pablo A. Gonzalez Garza
#500 Col. San Jerónimo
Monterrey, Nuevo León
Mexico.

ventas@gante.mx
gante.mx